

SORBERPOLY™ 3D AGC

polyester sound absorber with aluminium foil glass cloth facing

Sorberpoly[™] 3D AGC is a lightweight specialised acoustic textile made from ultra-fine polyester fibres to deliver excellent sound absorbing and thermal insulation properties.

Sorberpoly[™] 3D AGC has excellent fire and thermal insulation performance which is often required in rail and marine applications. This is achieved thanks to its durable, highly reflective aluminium faced glass cloth facing.

Manufactured from 100% recyclable polyester fibre, Sorberpoly™ 3D AGC is easy to use and is ideal for cavities and voids within heavy transport vehicles, trains and large boats. It's simple to install, safe to handle, and easily cut using scissors or a utility knife.

When compared to insulation of comparable acoustic performance, Sorberpoly™ 3D AGC is lighter than other absorbing mediums such as foam, rockwool and fibreglass. It meets or exceeds the needs of a variety of manufacturing and installation approaches.

VOC, ODP, HEALTH AND SAFETY

Sorberpoly 3D AGC is non-toxic and safe to handle by methods prescribed in Safety datasheet. No Volatile Organic Compounds (VOC) are intentionally added to Sorberpoly 3D AGC during its manufacture when evaluated according to definitions as applied under the Australia National Pollutant Inventory, The Council of the European Union, Council Directive 1999/13/EC or the USA EPA regulation 40 CFR 51.100(s). No Ozone depleting substances are used during the manufacture of Sorberpoly 3D AGC.

SPECIFICATIONS

Colour	Dark grey Silver facing
Available	Standard length: 20 m (65.6 ft) Standard width: 1.4 m (4.6 ft)
	Standard Thickness: 14 mm (0.55 in), 25 mm (1 in), 50 mm (2 in)
	Custom kit and sizes available depending on MOQ



applications

- Marine vessels, truck/bus cabins, railway and industrial vehicles
- HVAC systems/equipment
- Compressor, generator, hydraulic pump, machinery and equipment enclosures
- Heavy duty truck, earthmoving & mining equipment, wall, roof, firewalls and bonnet liners
- Acoustic enclosures, control rooms and compartments
- Specialised acoustic panels

features

- Lightweight with premium sound absorption
- Complies to international standards with excellent fire and toxicity ratings
- Resists weather, water and UV pollution over an extended period of time
- Excellent thermal insulator
- Durable, compressible, flexible
- Non-toxic and safe to handle without protective clothing or respiration apparatus, will not irritate skin
- · Light and heat reflective impermeable AGC facing
- Simple to install or retrofit
- Does not hold water
- · Made from recyclable polyester
- Mildew and odour resistant







PRODUCT SPECIFICATIONS

Product name	Standard Thickness	Roll size		Moisture		Operating
		Length	Width ¹	absorption ² (WSS M99P32-B)	Density ²	temperature range ³
Sorberpoly 3D AGC 14	14 mm (0.55 in)	20 m (65.6 ft)	1.4 m (4.6 ft)	2% at 38 °C, 98% RH (for 24 hrs) (Report No. 02015BD)	24 kg/m³ (1.5 lb/ft³)	-40 to 130 °C (-40 to 266 °F)
Sorberpoly 3D AGC 25	25 mm (1 in)					
Sorberpoly 3D AGC 50	50 mm (2 in)					

Tolerance: Thickness ± 2 mm (0.08 in); 1 Useable width: Some surface coverings may overhang the useable width. 2 For plain polyester only. 3 Higher temperatures can be suitable depending on the application.

All above products are available with pressure-sensitive adhesive backing. Under extreme temperature conditions or where the substrate surfaces cannot be free from contaminants, mechanical fixing will be required on vertical surfaces. For all inverted installations including ceiling installations, mechanical fixing must be done in addition to PSA adhesion. Please consult your local Pyrotek representative for more information.

MATERIAL PROPERTIES


Test method	Property	Report	Result	
EN 45545-2 (ISO 5658-2)	Spread of flame	340584		
EN 45545-2 (ISO 5659-2: 50 kWm ⁻²)	Heat release rate by cone calorimeter	339970	R1 (HL1, HL2, HL3)	
EN 45545-2 (ISO 5660-1: 50 kWm ⁻²)	Smoke generation (optical density)	339969		
FMVSS-302	Automotive burn rate	22315JY	Self-extinguishing	
ASTM C518*	Thermal conductivity	DI0519/DU01	0.0399 W/mK	

^{*}Plain Sorberpoly 3D

ACOUSTIC PERFORMANCE

Frequency (Hz)	Sorberpoly 3D AGC 14 mm	Sorberpoly 3D AGC 25 mm	Sorberpoly 3D AGC 50 mm
100	0.03	0.07	0.17
125	0.05	0.10	0.27
160	0.09	0.16	0.37
200	0.13	0.31	0.83
250	0.21	0.53	0.61
315	0.26	0.79	0.51
400	0.37	0.76	0.73
500	0.57	0.40	1.09
630	0.81	0.32	0.54
800	0.54	0.49	0.33
1000	0.35	0.88	0.49
1250	0.44	0.98	0.79
1600	0.82	0.57	0.43
2000	0.73	0.44	0.33
2500	0.47	0.40	0.26
3150	0.34	0.35	0.21
4000	0.30	0.32	0.20
5000	0.25	0.24	0.19
NRC	0.45	0.55	0.65
SAA	0.48	0.57	0.58
$a_{_{\rm w}}$	0.45	0.45 (LM)	0.35 (LM)





For further information and contact details, please visit our website pyroteknc.com Caveats: Specifications are subject to change without notice. The data in this document is typical of average values based on tests by independent laboratories or by the manufacturer and are indicative only. Materials must be tested under intended service conditions to determine their suitability for purpose. The conclusions drawn from acoustic test results are as interpreted by qualified independent testing authorities. Nothing here releases the purchaser/user from responsibility to determine the suitability of the product for their project needs. Always seek the opinion of your acoustic, mechanical and fire engineer on data presented by the manufacturer. Due to the wide variety of individual projects, Pyrotek is not responsible for differing outcomes from using their products. Pyrotek disclaims any liability for damages or consequential discs as a result of reliance solely on the information presented. No warranty is made that the use of this information or of the products, processes or equipment to which this information or Rege relear within to Infininge any third party's patents or rights.

DISCLAIMER: This document is covered by Pyrotek standard Disclaimer, Warranty and © Copyright clauses. See pyrotekn.ccom/disclaimer.



